

In the Claims:

What is claimed is:

- 1.(Currently Amended) A method of reducing ~~affects~~ the effect of linear birefringence in an optical fiber, comprising:
 - (a) ~~subdividing~~ heating a length of the optical fiber; ~~into a plurality of sections;~~ and
 - (b) introducing into the length of said fiber ~~between the sections~~ a twist having a predetermined sense of rotation and a twist angle, thereby creating a plurality of sections in said fiber.
2. (Original) The method of claim 1, further comprising reversing the sense of rotation of the twist between sections after an accumulated twist for previously introduced twists between sections is substantially equal to 90°.
3. (Currently Amended) The method of claim 2, wherein the twist angle between respective ends of the adjacent sections is substantially 90°.
4. (Currently Amended) The method of claim 2, wherein the twist angle between respective ends of the adjacent sections is less than 90°.
5. (Currently Amended) The method of claim 2, wherein the twist angle between respective ends of the adjacent sections is greater than 90°.
6. (Currently Amended) The method of claim 1, wherein a fiber orientation is maintained along the plurality of sections separated by said twist.
7. (Original) The method of claim 6, further comprising reversing the sense of rotation of the twist between sections after an accumulated twist for previously introduced twists between sections is substantially equal to 90°.
8. (Currently Amended) The method of claim 7, wherein the twist angle between respective ends of the adjacent sections is substantially 90°.

9. (Currently Amended) The method of claim 7, wherein the twist angle between respective ends of the adjacent sections is less than 90°.

10. (Currently Amended) The method of claim 1, wherein the twist angle between respective ends of the adjacent sections is less than 90°.

11. (Currently Amended) The method of claim 1, wherein the twist angle between respective ends of the adjacent sections is substantially equal to 90°.

12. (Canceled)

13. (Original) The method of claim 1, wherein a cumulative retardance along each of the sections is less than 180°.

14. (Currently Amended) An optical fiber with reduced effects of linear birefringence, comprising:

a length of optical fiber, wherein said fiber comprises a twist separating said fiber into (a) a plurality of fiber sections, and; wherein said twist is formed by heating said fiber. (b) a twist located between adjacent sections.

15. (Original) The optical fiber of claim 14, wherein a sense of rotation of the twist between sections along the optical fiber is reversed after an accumulated twist for previously introduced twists between sections is substantially equal to 90°.

16. (Currently Amended) The optical fiber of claim 14, wherein a twist angle between respective ends of the adjacent sections is substantially equal to 90°.

17. (Original) The optical fiber of claim 14, wherein the optical fiber is a circular-cored single-mode fiber.

18. (Currently Amended) The optical fiber of claim 14, wherein an orientation of the fiber is maintained along the plurality of sections separated by said twist.

19. (Currently Amended) The optical fiber of claim 18, wherein a sense of rotation of the twist between sections along the optical fiber is reversed after an accumulated twist for previously introduced twists between sections is substantially equal to 90°.

20. (Currently Amended) The optical fiber of claim 19, wherein a twist angle between respective ends of the adjacent sections is substantially equal to 90°.

21. (Currently Amended) The optical fiber of claim 19, wherein a twist angle between respective ends of the adjacent sections is less than 90°.